

# Gamma Wipe® 67

## Steril renrumsklud

- Fremstillet af 55% cellulose og 45% polyester
- Gamma steriliseret
- · Kraftigt absorberende
- Ingen bindemidler eller andre additiver
- Kan anvendes med almindelige rengørings- og desinfektionsmidler
- Renrums klasse 100



Varenummer	Størrelse	Navn	Pakning
673030	30 x 30 cm	Gamma Wipe 67	500 / kt



# Gamma Wipe® 67

### Sterile Polyester / Cellulose Nonwoven Wiper

Gamma Wipe®67 is a polyester / cellulose blend wiper recommended for ISO Class 5 and above environments composed of 45% polyester and 55% cellulose. Each package is gamma irradiated to a 10° Sterility Assurance.

This combination of properties provides Gamma Wipe® 67 with the level of cleanliness, abrasion resistance and chemical compatibility required for cleaning general sterile processing areas where both economy and cleanliness are required.



#### Other Sterile wipers

- Gamma Wipe SuperSorb®
- Gamma Wipe® 300
- Gamma Wipe® 120

#### **Key Attributes**

- 55% cellulose / 45% polyester hydroentangled nonwoven
- No secondary binders
- Gamma irradiated and sterile validated to a 10<sup>-6</sup> Sterility Assurance Level per AAMI guidelines
- Header style packaging with Package Integrity testing
- Lot number on each pack
- Certificate of Sterility with each case and available on the web by lot number 24/7. Details: Expiration Date, Radiation Dosage, Lot Information, Meets cGMP requirements for traceability

#### **Benefits**

- Excellent combination of the synthetic polyester strength and cleanliness with the absorbent characteristics of cellulose.
- Smooth, highly absorbent and durable with low extractable levels
- Economica
- Chemically compatible with common cleaning and disinfecting solutions including isopropyl alcohol, phenols, bleaches and quarternary ammonium compounds

#### Applications

- $\bullet \qquad \text{Designed for use in ISO Class 5 and higher sterile environments and USP\,<797>\, applications$
- Designed for cleaning sterile surfaces and equipment during aseptic processing
- General wiping in component prep, compounding and wash areas
- General wipedowns in sterile gowning rooms
- Applying and removing cleaning and disinfecting solutions

#### **Technical Data:**

Attribute		Units	Value	Test Method
Basis Weight		g/m²	67.6	TAPPI T-410
Caliper		μm	243	TAPPI T-411
Fibers	≥100µm	fibers/cm <sup>2</sup>	200	IEST-RP.CC004.3, Sec 6.1.3 / Sec 6.2.2
Particles	≥0.5µm	x10 <sup>3</sup> /cm <sup>2</sup>	16	IEST-RP.CC004.3, Sec 6.1.3 / Sec 6.2.1
Sorbency	Capacity	mL/m²	291	IEST-RP.CC004.3, Sec 8.1 modified / Sec 8.2 modified
	Efficiency	mL/g	4.3	
	Rate	seconds	2	
Non-Volatile Residue	DI Water	g/m²	0.030	IEST-RP.CC004.3, Sec 7.1.2
	IPA	g/m²	0.0034	
lons	Na <sup>+</sup>	ppm	49	IEST-RP.CC004.3, Sec 7.2.2
	K <sup>+</sup>	ppm	4.1	
	Ca <sup>++</sup>	ppm	12	
	Mg <sup>++</sup>	ppm	4.7	
	Cl	ppm	39	